



Description

Condensate Polishing- Highest capacity lowest TOC mixed bed intended for final polishing in secondary loops

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure		Styrene-DVB
Appearance		yellow spherical beads
Type		Gel mixed bed resin
Ionic form		H ⁺ /OH ⁻
Moisture Content	%	50-55% (H ⁺) 53-58% (OH ⁻)
Total Exchange Capacity	Eq/L	
	Cation (in sodium form)	2.0
	Anion (in chloride form)	1.4
Particle Size Range	0.315-1.25mm	≥95
Uniformity Coefficient	max.	≤1.6
Shipping Weight	g/ml	0.70-0.74
Temperature Limited	°C	60
Whole Spherical Rate After Attrition	%	≥90

TYPICAL PACKAGING

- 25L PE bag
- 1 Cubic feet
- 1000L Super Sacks