



Description

Condensate Polishing- Highest capacity lowest TOC mixed bed intended for final polishing in secondary loops

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Styrene-DVB
Appearance	yellow spherical beads
Type	Gel mixed bed resin
Ionic form	H ⁺ /OH ⁻
Moisture Content %	50-55% (H ⁺) 53-58% (OH ⁻)
Total Exchange Capacity Eq/L	
Cation (in sodium form)	2.0
Anion (in chloride form)	1.4
Particle Size Range 0.315-1.25mm	≥95
Uniformity Coefficient max.	≤1.6
Shipping Weight g/ml	0.70-0.74
Temperature Limited °C	60
Whole Spherical Rate After Attrition %	≥90

TYPICAL PACKAGING

- 25L PE bag
- 1 Cubic feet
- 1000L Super Sacks